### skheme®

# **Alpes Max**



Made in Italy, ALPES MAX Series combines stone, marble and metal textures to create a crossover style ideal for most designs. Their large slab formats allow it to be used in residential and commercial spaces. Available in four colours and three versatile sizes.

PRODUCT TYPE:	7mm coloured body porcelain slab
COLOURS:	lvory, Sand, Grey and Lead
SIZES:	1200x1200mm,1200x2400mm and 1600x3200x6mm Rectified edges
FINISHES/USAGE:	Natural/Wall and Floor
AESTHETIC QUALITIES:	Metal and Natural Stone look slabs
VARIATION:	

V2



Slim porcelain slabs allowing endless custom design opportunities such as joinery cladding, internal and external facades.



Resistant to stain/

chemical agents



Record dimensions, up to 1600x3200mm

To easily renovate floors and walls




ECOLOGIA ECOLOGY

Slab only 7mm thick

New eco-friendly technology





indoor floors/walls

glued and ventilated exterior facades

bathroom/kitchen shelves








### skheme®


#### **PRODUCT SPECIFICATIONS**

SIZES	FINISHES	SLIP RATING	TILE EDGE
1200x1200mm*	NATURAL	-	RECTIFIED
1200x2400mm	NATURAL	-	RECTIFIED
1600x3200mm*	NATURAL	-	RECTIFIED

\*Indent item - Subject to stock availability overseas, please allow 10-12 weeks lead time from date of order confirmation. Minimum quantity may apply.

#### FORMATS





1600x3200x6mm

1200x2400mm 1200x1200mm **IVORY** 






### skheme®


#### PRODUCT SPECIFICATIONS

SIZES	FINISHES	SLIP RATING	TILE EDGE
1200x1200mm*	NATURAL	-	RECTIFIED
1200x2400mm*	NATURAL	-	RECTIFIED
1600x3200mm*	NATURAL	-	RECTIFIED

\*Indent item - Subject to stock availability overseas, please allow 10-12 weeks lead time from date of order confirmation. Minimum quantity may apply.

#### FORMATS





1600x3200x6mm

1200x2400mm 1200x1200mm



# **Alpes Max**



SAND

GREY



### TECHNICAL SPECIFICATIONS

Technical Characteristis	Test Standard	Product Standard	Result
Length and Width	ISO 10545-2+	/-0,6% (+/-2mm)	Complies
Thickness	ISO 10545-2	+/-0,5% (+/-5mm)	Complies
Straightness of sides	ISO 10545-2	+/-0,5% (+/-1,5mm)	Complies
Rectangularity	ISO 10545-2	+/-0,5% (+/-2mm)	Complies
Water Absorption	ISO 10545-3	Eb 0,5%	Eb 0,3%
Breaking Strength	ISO 10545-4	min 1300	>1500
Modulus of Rupture	ISO 10545-4	min 35	45
Warp	ISO 10545-2	Deviation % Max ‡ 0,5	Complies
Thermal Shock	ISO 10545-9	Test method available	Resistant
Frost Resistance	ISO 10545-12	Required	Resistant
Resistance to household chemicals	ISO 10545-13	min GB	min GA



#### **VARIATION - IVORY**





### **VARIATION - LEAD**





### **VARIATION - SAND**





#### **VARIATION - GREY**





